




Zibo Yolite Composite Materials Co.,Ltd.
Add: No.18 Xingu Road, Linzi District, Zibo,
Shandong, China.
Web: www.yolite.asia




Zibo Yolite Composite Materials Co.,Ltd.
Tel: +86-533-7361217; 7227217
Fax: +86-533-7360161
Mail : info@yolite.asia

→Copolymer coaed Steel Tape



Type	Standard	Thickness			Color
EGE-25	YD/T723.3-2007	Steel	EAA	Total	White, Green
		0.155±0.005	0.05±0.005	0.255±0.01	
Property		Unit	Typical value		Test method
Tensile Strength		MPa	310-390		ASTM E8
Elongation at break		%	15		ASTM E8
Peel strength		N/cm	6.13		ASTM B736
Heat seal strength		N/cm	17.5		ASTM B736
Filler/Floodant Resistance			No delamination		REA PE-39, PE-89
68±1°C,168hrs					
Water Resistance					
68±1°C,168hrs					
Peel strength		N/cm	6.13		ASTM B736
Dielectric Strength					
Two-side, DC 2KV, 1'					No break
Corrosion Resistance		Grade	7		

→Aluminium copolymer tape



Type	Standard	Thickness			Color
ELE/EL	YD/T723.2-2007	Aluminum	EAA	Total	Natural, Blue
		0.15,0.20	0.05	0.20,0.25	
Property		Unit	Typical value		Test method
Tensile Strength		MPa	≥65		ASTM E8
Elongation at break		%	≥15		ASTM E8
Peel strength		N/cm	≥6.13		ASTMB736
Heat seal strength		N/cm	≥17.5		ASTMB736
Filler/Floodant Resistance			No delamination		REA PE-39, PE-89
68±1°C,168hrs					
Water Resistance					
68±1°C,168hrs					
Peel strength		N/cm	≥6.13		ASTM B736
Dielectric strength					
Two-side, DC 1KV, 1 min					No break
Corrosion Resistance		Grade	7		